

3. (Amended) The plastics-covered metal plate set forth in Claim 2 wherein the elongation rate of the plastic film (B) is larger than the elongation rate of the plastic film (A) by at least 10%.

4. (Amended) The plastics-covered metal plate set forth in Claim 2 wherein the elongation rate of the plastic film (B) is larger than the elongation rate of the plastic film (A) by at least 50-200%.

5. (Amended) The plastics-covered metal plate set forth in Claim 2 wherein the elongation rate of the plastic film (A) is 1-100%.

6. (Amended) The plastics-covered metal plate set forth in Claim 2 wherein the elongation rate of the plastic film (A) is 5-70%.

7. (Amended) The plastics-covered metal plate set forth in Claim 2 wherein the oxygen permeability of the plastic film (A) in its single coating film form at 25°C is less than $10^{-11} \text{cm}^3 \cdot \text{cm} / \text{cm}^2 \cdot \text{sec} \cdot \text{cmHg}$.

8. (Amended) The plastics-covered metal plate set forth in Claim 2 wherein the oxygen permeability of the plastic film (A) in its single coating film form at 25°C is less than $10^{-12} \text{cm}^3 \cdot \text{cm} / \text{cm}^2 \cdot \text{sec} \cdot \text{cmHg}$.

9. (Amended) The plastics-covered metal plate set forth in Claim 2 wherein a plastic film (A) is further laminated at the lower plastic film (B) (at the nearer side to the metal plate).

10. (Amended) The plastics-covered metal plate set forth in Claim 1 wherein the plastic film is formed of a thermoplastic resin selected from the group consisting of polyolefin resin, polyester resin, polycarbonate resin, epoxy resin, vinyl acetate resin, vinyl chloride resin, fluorine-

containing resin, polyvinyl acetal resin, polyvinyl alcohol resin, polyamide resin, polystyrene resin, acrylic resin, polyurethane resin, phenolic resin, polyether resin, and cellulose type resin.

11. (Amended) The plastics-covered metal plate set forth in Claim 1 wherein the thickness of each plastic film is in the range of 1-100 μm .

12. (Amended) The plastics-covered metal plate set forth in Claim 1 wherein the thickness of each plastic film is in the range of 5-50 μm .

13. (Amended) The plastics-covered metal plate set forth in Claim 1 wherein the thickness of each plastic film is in the range of 5-120 μm .

14. (Amended) The plastics-covered metal plate set forth in Claim 1 wherein an adhesive exists between a plastic film and the metal plate and between each other plastic film.

19. (Amended) A car body comprising partly or totally the plastics-covered metal plate set forth in Claim 1.